



**Resistance to humidity (liquid and marine environments).**

**Resistance to UV (outdoor applications).**

- Closure consisting of 2 woven tapes :
  - mono-filament hooks
  - non-brushed loops.
- Material : 100% polyester
- Available in fire retardant version.
- Methods of attachment : bonding, sewing, welding or stapling.
- Widths : 25 and 50mm (other widths on request).
- Colours : 000 008

## PERFORMANCE DATA

**S**  
**T**  
**R**  
**E**  
**N**  
**G**  
**T**  
**H**  
**S**

		New state	10 000 cycles
Peel Strength <small>(N/cm) as defined by EN 12 242</small>		1.3	1
Shear Strength <small>(N/cm²) as defined by EN 13 780</small>		14	9
Traction Strength <small>(N/cm²) as defined by NF G91-103</small>		6	5

*NB : The results shown above are average values obtained from 25mm-wide tapes.*

FTC/EN/IND/aplix® 810 / Page1/2 - 05/03/2013

## TECHNICAL CHARACTERISTICS

### Physical characteristics

- Thickness of the closure: 3 mm (hook: 2 mm / loop: 2.7 mm)
- Weight of the closure: 0.064 g/cm<sup>2</sup>
- Width of the selvedge: 2 mm
- Breaking point of the tape: >200 N/cm.

### Effects of temperature

- Resistance to temperature: 140 °C.
- Improved performance in cold conditions.
- Melting point: 255 °C.

### Reaction to liquids

- Maximum shrinkage in boiling water: < 2%.
- Resistant to seawater.

### Reaction to chemical products

- Resistant to low acids and alkalis, trichloroethylene and hydrocarbons.
- Sensitive to strong acids and alkalis, and alcohols.

### Cleaning

- Washing at 60 °C.
- Dry cleaning.
- Drying and ironing in the closed condition.

**NB** : These characteristics are only valid for standard products (non adhesive products).

## PACKAGING

### Widths

25 ml

25 mm

250 ml

50 mm

200 ml

## APPROVALS AND STANDARDS (for fire retardant version)

### AIRCRAFT

FAR/EASA CS 25-853 Appendix F Part 1 (a)(1)(ii) 12s

BMS 8-285 J

### AUTOMOTIVE

FMVSS-302